



HOUILLÈRES de CRUÉJOULS

TECHNICAL DATASHEET

DATE EDITED: 09/06/2010

DATE UPDATED: 06/12/2010

VERSION: 03

Béton déco Finition

AREAS OF USE

Interior and exterior decoration.
Walls and furniture.

CHARACTERISTICS

Decorative micro-mortar giving an authentic waxed concrete appearance.

COMPOSITION

Cement, marble powder, talc, adjuvants.
Mineral pigments according to colour.

SHADES

Natural white, natural grey or as per **Béton déco finition** colour chart.

It is also possible to mix shades together to create new shades using our pigments.

EQUIPMENT

Plastering trowel, spatula, mechanical mixer.
Glanes and protection sunglanes.

PREPARATION OF SURFACES

Ideally, the surface must be sound, dry and clean.

■ **On standard surfaces** (plasterboard, plaster, cement rendering, concrete, old paint, etc.): apply our **Sous-couche acrylique granitée** (Acrylic granite-finish primer).

For humid environments (bathroom, shower, sauna...), first protect the surface against humidity with a suitable product. Our **Béton déco finition** must never be used as waterproof lining.

■ **On old tiling, on earthenware, concrete or earth bricks, cellular concrete or agglomerated wood panels**, apply specific screeding or use a tile glue.

PREPARATION OF THE RENDER

Mix 1 litre of **Sup-Latex** with 0.5 litre of water.

Mix 5 kg of **Béton déco finition** with the solution prepared by hand or using a mechanical mixer on very slow speed.

Optionally, gradually add a little water to obtain the desired consistency (do not exceed 0.5 litre of water).

It is advisable only to mix 5 kg at one time.

It is possible to make a thicker mixture for the first coat, then a more liquid mixture for the second coat.

To create new shades, a medium hue is obtained with 50 g of pigment per 5 kg of **Béton déco finition Blanc naturel**. Over and above 100 g of pigment, a phenomenon of chalking may occur.

Some pigments (oxides and some mixtures) may leave traces of brighter colour (streaks). To reduce this risk, it is advisable to prepare a pigment paste. To form this pigment paste, the entirety of the pigment or pigments must be mixed with part of the mixing water and a few drops of wetting agent. The more this paste is worked in before mixing with **Béton déco finition**, the lesser the risk of streak-formation.

APPLICATION

It is advisable to carry out tests before applying to a large surface area.

Room temperature: 10°C to 30°C.

Apply with a stainless steel trowel or spatula in a very thin layer.

A second coat can be applied at least after 24 hours to obtain different effects.

A highly marbled, veined appearance can be obtained with two coats if the first coat has reliefs (sharp points are to be sanded down with very fine sandpaper after 24 hours' drying time before applying the second coat).

A more blended appearance can be obtained with a first coat that is as planar as possible.

The second coat can be burnished to give a stucco appearance.

DÉFI - HOUILLÈRES DE CRUÉJOULS

ZI La Gloriette - 38160 Chatte - France

Tél. 33 (0)4 76 64 85 64 - Fax 33 (0)4 76 64 85 69 - Email defi.h2c@orange.fr

Siret 331 014 993 000 58 RCS Grenoble - Code APE 4669B - N° TVA FR22331014993 - SAS au capital de 912 356 euros



HOUILLÈRES de CRUÉJOULS

FINISHED APPEARANCE

Apply our **Profinish** or **Cire incolore pour sol béton** (colourless wax for concrete flooring) using a wide brush, in two coats leaving the surface to dry 6 to 12 h between each coat.

It is possible to polish after drying to achieve a shine.

YIELD

Approximately 0.8 kg per m² for one 1,5 mm coat (6 m² with 5 kg of **Béton déco finition**).

Consumption may vary depending on the desired finish and on surface condition.

CLEANING

With water.

PRECAUTIONS FOR USE

Work in a ventilated area and wear a dust mask to avoid any irritation due to the presence of cement. Refer to the cautionary advice on the label.

MAINTENANCE

The **Profinish** or **Cire incolore pour sol béton** can be used for maintenance and easy cleaning of the surfaces.

STORAGE

Store in a dry, cool place in the original, closed packaging.

IMPORTANT

The indications given are based on our state of knowledge of the products concerned and do not under any circumstance entail the providing of any guarantee. It is for users to carry out tests prior to use and to take the necessary safety precautions.

DÉFI - HOUILLÈRES DE CRUÉJOULS
ZI La Gloriette - 38160 Chatte - France

Tél. 33 (0)4 76 64 85 64 - Fax 33 (0)4 76 64 85 69 - Email defi.h2c@orange.fr

Siret 331 014 993 000 58 RCS Grenoble - Code APE 4669B - N° TVA FR22331014993 - SAS au capital de 912 356 euros